AMENDMENT TO THE CLAIMS

Please replace the claims with the following rewritten listing:

1. (Currently Amended) A multilayer product comprising~~,~~: ~~on~~

a polymer substrate,

a wear layer made of polymer of ~~the~~ an ionomeric type, ~~characterized in that it comprises~~and,

between the substrate and the wear layer, an intermediate layer of an olefinic polymer containing from 1 to 40 parts by weight of a metallocene per 100 parts by weight of the olefinic polymer.

2. (Currently Amended) The product according to claim 1, ~~characterized in that~~wherein the polymer substrate and the polymer of the ionomeric type comprise olefinic polymers.

3. (Currently Amended) The product according to claim 2, ~~characterized in that~~wherein the olefinic polymers of the substrate and of the intermediate layer comprise low-density polyethylene.

4. (Currently Amended) The product according to ~~any one of~~ claims ~~1 to 3~~, ~~characterized in that~~wherein the intermediate layer contains from 5 to 30 parts by weight of metallocene per 100 parts by weight of the olefinic polymer.

5. (Currently Amended) The product according to claim 4, ~~characterized in that~~wherein the intermediate layer contains from 8 to 15 parts by weight of metallocene per 100 parts by weight of the olefinic polymer.

6. (Currently Amended) The product according to ~~any one of~~ claims ~~1 to 5~~, ~~characterized in that~~further comprising an additional layer of low-density ethylene polyolefin ~~is placed~~ between the substrate and the intermediate layer.

7. (Currently Amended) The product according to claim 6, ~~characterized in that~~wherein the additional layer comprises low-density polyethylene and, where appropriate, one or more additives chosen from the group consisting of fatty acids and silica.

8. (Currently Amended) The product according to any one of claims 1 ~~to 7~~, ~~characterized in that it comprises~~further comprising a surface layer made of polyurethane on the wear layer.

9. (Currently Amended) ~~The~~ A process for manufacturing a multilayer product comprising: ~~according to any one of claims 1 to 8, according to which~~

extruding a parison comprising a layer of an olefinic polymer containing a metallocene and an outer layer made of polymer of ~~the~~ an ionomeric type wherein the parison is extruded by blow-molding to form a bubble,

crushing the bubble collected from the blow-molding extrusion ~~is crushed~~ to obtain a doubled film,

separating the doubled film ~~is separated~~ to obtain two separate multilayer films, and

fixing one of the films ~~is fixed~~ onto a substrate.

10. (Currently Amended) The process according to claim 9, ~~characterized in that~~ anwherein the outer layer made of polyolefin~~, preferably an outer layer made of low-density polyethylene~~, is extruded onto ~~the~~ an intermediate layer of an olefinic polymer containing a metallocene.

11. (Currently Amended) The process according to claim 9 ~~or 10~~, ~~characterized in that~~wherein the blow-molding of the parison is regulated such that ~~the~~ a circumference of the bubble measures at least 8 m and ~~its~~ a thickness is from 150 to 250 μm.

12. (Currently Amended) The ~~use of a product~~process according to ~~any one of~~ claims ~~1 to 8~~ 9 ~~for the manufacture of~~ further comprising applying the product as a floor or wall coverings.

13. (New) The process according to claim 10, wherein the outer layer is made of a low density polyethylene.

14. (New) A multilayer product comprising:

a substrate;

a wear layer; and

an intermediate layer disposed between the substrate and the wear layer; wherein, the intermediate layer comprises an olefinic polymer containing from 1 to 40 parts by weight of a metallocene per 100 parts by weight of the olefinic polymer.